

PTO 95-6020

Japan, Kōkai
Sho 63-299971 (A)

INK-JET RECORDING METHOD
[Inkujetto Kiroku Hōho]

Tamotsu Aruga et al.

UNITED STATES PATENT AND TRADEMARK OFFICE

Washington, D.C.

September 1995

Translated by: Schreiber Translations

Country : Japan
Document No. : Sho 63-299971(A)
Document Type : Kōkai
Language : Japanese
Inventor(s) : Tamotsu Aruga, Kakuji Murakami,
Katsu Shimada, Kiyofumi Nagai,
Hiroyuki Kamimura
Applicant(s) : Ricoh K.K.
IPC : B41M 5/00, B41J 3/04, C09D 11/00
Application Date : May 30, 1987
Publication Date : December 7, 1988
Foreign Language Title : Inkujetto Kiroku Hōho
English Title : INK-JET RECORDING METHOD

1. Title: INK-JET RECORDING METHOD

2. Claims 1. An ink-jet recording method characterized in that after adhering to a recording medium a colorless or light-colored liquid containing an organic compound having two or more cationic groups per molecule, an image is formed by adhering ink containing an anionic dye to the portions on which said liquid has been adhered.

2. The recording method of claim 1 wherein said colorless or light-colored liquid contains a penetrant.

3. The recording method of claim 2 wherein said penetrant is one or more members chosen from among the group consisting of nonionic surfactants, anionic surfactants, cationic surfactants, and fluorine surfactants.

4. The recording method of claim 1 wherein said colorless or light-colored liquid contains a polyhydric alcohol.

5. The recording method of claim 1 wherein said colorless or light-colored liquid is pH 5-14 or above.

6. The recording method of claim 1 wherein the surface tension of said ink is 50 dyne/cm or less.

7. The recording method of claim 1 wherein said anionic dye contains an intramolecular acid radical in the form of $-\text{SO}_3^-$, $-\text{COO}^-$, or $-\text{O}^-$.

3. Detailed Description of the Invention

¹ Numbers in the margin indicate pagination in the foreign text.

Industrial Field

The present invention relates to an ink-jet recording method, and more specifically, to an ink-jet recording method in which, prior to the spraying of ink from a nozzle, a colorless or light-colored liquid is adhered to the recording medium to ensure good fixation of the ink.

Prior Art

Recently, the advantages of ink-jet recording methods have led to their extensive utilization. These advantages lie in that ink-jet recording methods: (a) permit high-speed recording, (b) permit the use of various types of paper, including common paper, as the recording medium since there is no contact with the recording medium, and (c) permit color printing. /458

However, the problem of nozzle clogging in ink-jet printing methods remains. To solve this problem, in addition to working on the shape and structure of the nozzle tip, the use in the ink of a dye with a high degree of solvent solubility is also considered necessary. However, the durability (resistance to water when the solvent is water) of images obtained when using normal dyes of high solvent solubility in the ink tends to be poor.

Proposed methods of eliminating this drawback are (1) precoating a material to fix the dye on the recording paper (recorded in Unexamined Japanese Patent Publication Nos. 56-86789, 55-144172, 56-84992, etc.) and (2) providing a water-resisting agent forming a lake with the dye in the printed image

(recorded in Unexamined Japanese Patent Publication No. 55-150396). However, above-cited method (1) requires the use of special recording paper as the recording medium. Although above-cited method (2) solves the problem of water resistance, since it is little effective or completely ineffective with regard to the drying property of the image after printing, the image resolution, and the image density, the result is a recording medium of extremely limited application.

When the inks that have been employed in ink-jet recording methods to-date are printed on the recording paper (recording medium) commonly employed in offices, their drying times are slow, greasing and smearing caused by offsets in the recording paper feed system occur, and, particularly in the case of color recording, since the quantity of ink applied per unit area of recording paper (recording medium) is large (due to the overlapping of multiple colors), there is a drawback in that the ink flows into areas in which it is not required, blurring the image.

Proposed methods of solving this drying property problem include: (3) the use of paper to which no or little sizing has been added as the recording medium (recorded in Unexamined Japanese Patent Publication No. 52-74340), (4) the use of paper on the surface of which is applied a coating consisting chiefly of white pigment or a water-soluble polymeric material as the recording medium (recorded in Unexamined Japanese Patent Publication Nos. 52-53012, 56-89594, etc.), (5) the addition to

the ink of a compound such as a surfactant to raise the penetration of the ink, thereby lowering the ink surface tension (recorded in Unexamined Japanese Patent Publication No. 55-65269), (6) the use of an ink consisting chiefly of an organic solvent such as an alcohol, ketone, or the like with a low surface tension, (7) use of an ink consisting chiefly of a volatile solvent (recorded in Unexamined Japanese Patent Publication No. 55-65976), and (8) circulating the ink during use. However, above-cited methods (3) and (4), similar to above-cited method (1), require the use of a special recording medium. Although the drying property is slightly improved by above-cited methods (5) and (6), since the ink medium (carrier) and the dye in the ink penetrate deeply into the recorded image, there are drawbacks in that the dye tends to penetrate through to the back side of the recording paper, lowering the image density and tending to decrease image definition. Due to increased wetting of the recording surface, drawbacks such as feathering and decreased resolving power (the ink spreads across the surface and dot diameters increase in size) occur. In above-cited method (7), the penetration of ink into the recording paper is accelerated while evaporation of solvent from the surface of the recording paper tends to occur, achieving satisfactorily rapid drying. However, in addition to the same drawbacks as in above-cited method (6), the nozzles tend to clog due to evaporation of solvent. In above-cited method (8), the solvent is evaporated by circulation of the ink. This changes the ink composition, which

has the drawback of either precluding printing entirely or necessitating a complex configuration to compensate for the change in ink composition.

A proposed method of increasing the sharpness of the printed image is (9) prespraying a solution of a polymer such as carboxymethyl cellulose, polyvinyl alcohol, or polyvinyl acetate onto the recording medium prior to printing (recorded in Unexamined Japanese Patent Publication No. 56-89595). Although method (9) effectively increases sharpness, there are drawbacks in that the high viscosity of the polymer solution makes for poor drying of the solution itself and the drying property of /459 the ink shows little improvement relative to when it is printed on normal paper.

Based on these problems, there is need for an improved ink-jet recording method in which the above-described drawbacks do not occur.

Object

The present invention, in accordance with the above-stated needs, has for its object to provide an ink-jet recording method improving the drying property, water resistance, light resistance, resolution, definition, sharpness, and the like of the image after printing, raising the image density after printing, preventing nozzle clogging, and improving printer reliability.

Configuration

The ink-jet recording method of the present invention is characterized in that after adhering a colorless or light-colored liquid containing an organic compound having two or more cationic groups per molecule to a recording medium, an image is formed by adhering ink containing an anionic dye to the portions on which the liquid has been adhered.

The present inventors discovered that when a colorless or light-colored liquid containing an organic compound having two or more cationic groups per molecule (hereinafter referred to sometimes as an "organic cationic compound-containing solution") is adhered to a recording medium, and, on the spots where the organic cationic compound-containing solution is adhered, ink containing anionic dye is provided as an image, the cationic groups in the cationic compound and the anionic groups in the dye combine, yielding an image formed of salts insoluble or little soluble in solvent. The present invention was devised on this basis.

The method of the present invention is described in greater detail below.

As set forth above, in the ink-jet recording method of the present invention, a colorless or light-colored liquid containing an organic cationic compound is first adhered to a recording medium.

Representative examples of this organic cationic compound are polymeric compounds having (a) primary, secondary, tertiary, or quaternary nitrogen (amine or ammonium) or phosphorus

(phosphonium) in their molecular chains or as pendant chains, and
(b) low molecular weight cationic organic compounds.

Below are specific examples of above-mentioned compound (a):

(1) (m=an integer of 0-3; R^1 , R^2 , R^3 =hydrogen or
lower alkyl groups)

(2)

(polyethyleneimine)

(3)

(polyethyleneimine)

(4)

(m and n are integers)

([illegible] polymer)

(5)

(R^4 is hydrogen or a lower alkyl group)

(polyvinyl pyridine)

(6) (R⁴ is hydrogen or a lower alkyl group)

(polyvinyl pyridine)

(7)

(aminoacetal-treated polyvinyl alcohol)

(8)

(polyvinyl imidazole)

(9) (R⁵ and R⁶ are lower alkyl groups)

(polydialkylallylammonium)

(10) (m is an integer of 0-3; R⁷, R⁸, and R⁹
are hydrogen or lower alkyl groups)

/460

(11) (m is an integer of 0-3; R¹⁰, R¹¹, and R¹²
are hydrogen or lower alkyl groups)

(12) (m is an integer of 0-3; R¹³, R¹⁴, and R¹⁵
are hydrogen or lower alkyl groups)

(13) (R¹⁶ and R¹⁷ are hydrogen or lower alkyl

groups)

(14) (R¹⁸ and R¹⁹ are hydrogen or lower alkyl groups)

(polyvinylbenzylphosphonium)

These polymeric cationic compounds can be employed as compounds of any acid, such as hydrochlorides, acetates, nitrates, and sulfates.

Examples of commercial products of the above-mentioned polymeric cationic organic compounds are: Sanfix 414, 414-C555, 555US, 70, and PRO-100 (from Sanyō Kasei); Protex 200, Fix K, H, SK, MCL, and FM (from Satoda Kakō);, Morinfixconk 3M (Morin Kagaku); Amigen (Daiichi Yakuhin Kōgyō); Epomin P100 (Nihon Shokubai); Fixoil R737 and E50 (Akinari Kagaku); Neofix RS (Nika Kagaku); Polyaminesulfone (Nittō Ketsu [illegible]); Polyfix 601 (Shōwa Kōbunshi); Nikafix D100 (Nihon Carbide); Rebogen B (Bayer); and Kaimen 557 (Dick Hercules).

The solubility of these polymeric cationic compounds deteriorates at higher molecular weights. Compounds with molecular weights of 100,000 or less are preferable for use in the method of the present invention to avoid solutions with excessively high viscosities. Compounds having 5-200 of the above-described cationic groups per molecule and a molecular weight of 20,000 or less are particularly desirable.

Specific examples of above-mentioned compound (b) are: aliphatic or alicyclic polyhydric amines such as ethylenediamine, hexamethylenetetramine, piperazine, 1-(2'-aminoethyl)piperidine, 1-(2'-aminoethyl)aziridine, 1-(2'-aminoethyl)pyrrolidine, 1-(2'-aminoethyl)hexamethyleneimine, hexamethylenediamine, diethylenetriamine, triethylenetetramine, tetraethylenepentamine, *N,N'*-bis(3-aminopropyl)putrescine, *N*-(3-aminopropyl)putrescine, 1,4-diazacycloheptane, 1,5-diazacyclooctane, 1,4,11,14-tetraazacycloeicosane, 1,10-diazacyclooctadecane, 1,7-diaminopropane-3-ol, 1-amino-2,2-bis(aminomethyl)propane-1-ol, 1,3-diaminopropane-2-ol, *N*-(2-oxypropyl)ethylenediamine, heptaethyleneoctamine, nonaethylenedecamine, 1,3-bis(2'-aminoethylamino)propane, triethylene-bis(trimethylene)hexamine, 1,2-bis-[3'-(2'-aminoethylamino)propylamine]ethane, bis(3-aminoethyl)amine, 1,3-bis(3'aminopropylamino)propane, and *sym*-homospermidine. Of these, compounds having three or more nitrogen atoms per molecule are particularly desirable for use in the method of the present invention. This is because compounds with two or fewer nitrogen atoms tend not to form insoluble combinations when they react with a dye. Furthermore, aromatic polyhydric amino acids such as phenylenediamine, triaminobenzene, tetraaminobenzene, pentaaminobenzene, hexaaminobenzene, 2,6- or — 2,5-diamino-*p*-benzoquinonediimine, and 2,3,7,8-tetraamino /461 phenazine can also be employed.

The methods of synthesizing these compounds are recorded in Barton, Ollis, *Comprehensive Organic Chemistry*, Peryamon Press

(1979), etc.

The proportion of an organic cationic compound synthesized in this manner that is incorporated into the colorless or light-colored liquid is not specifically limited. However, the compound is suitably used at a concentration yielding, per unit area of recording medium, a 1/10-100 equivalent, preferably a 1/2-10 equivalent, of the anionic groups in the dye of the ink applied later.

The organic cationic compound-containing solution must dry rapidly once applied to the recording medium, particularly when printing rapidly. Furthermore, the printed ink must penetrate rapidly. To satisfy these requirements, it is desirable to add a compound to the transparent liquid (organic cationic compound-containing solution) and/or ink to increase penetration of the ink into the recording medium.

Examples of penetration-enhancing compounds (penetrants) are: nonionic surfactants such as polyoxyethylene alkyl ethers, polyoxyethylene alkyl phenyl ethers, polyoxyethylene alkyl esters, polyoxyethylene alkyl sorbitan esters, polyoxyethylene alkyl amines, glycerin fatty esters, sorbitan fatty esters, propylene glycol fatty esters, and polyoxyethylene glycol fatty esters; anionic surfactants such as alkyl sulfates, polyoxyethylene alkyl ether sulfates, polyoxyethylene alkyl ether acetates, alkyl benzene sulfonates, *N*-acylamino acid salts, alkyl sulfosuccinates, and alkyl phosphates; cationic surfactants such as quaternary amines like benzalkonium salts, and fluorine

surfactants such as perfluoroalkyl phosphoric esters, perfluoroalkyl carboxylates, and perfluoroalkyl betaines.

Of these, specific examples of preferred penetrants are: diethylene glycol monobutyl ether, diethylene glycol monophenylether, propylene glycol monobutyl ether, and phosphorus surfactants. These have a substantial effect in raising penetration.

Although the quantity of penetrant added to the organic cationic compound-containing solution varies somewhat with the type of penetrant, a quantity of 30 weight percent or less, desirably 0.001-30 weight percent, and preferably about 0.1-15 weight percent is appropriate.

In addition, other conventional compounds added in normal ink-jet recording methods can be added in the same manner to the organic cationic compound-containing solution. Examples are viscosity adjusting agents, preservatives (including [illegible] agents), pH-adjusting agents, and ultraviolet-radiation absorbing agents.

The use of polyhydric alcohols as viscosity-adjusting agents is particularly desirable since they also prevent nozzle clogging. Examples of polyhydric alcohols are: ethylene glycol, diethylene glycol, triethylene glycol, tetraethylene glycol, polyethylene glycol, propylene glycol, dipropylene glycol, glycerin, diethanolamine, and triethanolamine. These polyhydric alcohols are suitably added in a proportion of 0-70 weight percent, with 5-35 weight percent being particularly desirable.

Viscosity-adjusting agents other than polyhydric alcohols include alkyl ethers of polyhydric alcohols such as diethylene glycol monomethylether, diethylene glycol monoethylether, triethylene glycol monomethylether; and [illegible] compounds such as *N*-methyl-2-pyrrolidone and 1,3-dimethylimidazolidinone. These /462 [illegible] are capable of [illegible] the above-mentioned organic cationic compounds well and are thus desirable. The use of ethylene glycol, diethylene glycol, and glycerin is particularly advantageous.

Compounds suitable for use as preservatives are sorbates, benzoates, sodium pentachlorophenate, sodium 2-pyridinethiol-1-oxide, 2,4-dimethyl-6-acetoxy-*m*-dioxane, and 1,2-benzthiazoline-3-one.

As pH-adjusting agents, alkali metal hydroxides such as sodium hydroxide and potassium hydroxide; alkali carbonates such as sodium carbonate and potassium carbonate; ammonium hydroxide; quaternary ammonium hydroxide; diethanolamine; and triethanolamine can be employed. Salts such as sodium phosphate and sodium nitrate can be added to further buffer the pH. The pH of the organic cationic compound-containing solution is determined so that the organic cationic compound does not precipitate, the organic cationic compound-containing solution does not permeate parts with which it comes into contact, and the like. Parts comprising the system must be selected for a pH suitable to the organic cationic compound employed. Accordingly, the organic cationic compound-containing solution suitably has a

pH of 5-14, preferably 12 or above. At a pH of 12 or above, the absorption rate of the organic cationic compound-containing solution into the recording medium and the subsequent absorption of ink that is applied are advantageously rapid.

Ink containing dye having anionic groups will be described next. Here, any dye that bonds with the cations of the organic cationic compound to form a salt that is insoluble or little soluble in solvent can be used. In particular, dyes having anionic groups such as intramolecular -SO_3^- , -COO^- , and -O^- are employed. For example, the color index categories of acid dyes, reactive dyes, and direct dyes have these acid radicals.

The following are specific examples of dyes.

Examples of acid dyes are: C.I. acid yellow 17, C.I. acid yellow 23, C.I. acid yellow 42, C.I. acid yellow 44, C.I. acid yellow 79, C.I. acid yellow 142, C.I. acid yellow 35, C.I. acid red 42, C.I. acid red 52, C.I. acid red 82, C.I. acid red 87, C.I. acid red 92, C.I. acid red 134, C.I. acid red 243, C.I. acid red 254, C.I. acid red 289, C.I. acid blue 1, C.I. acid blue 9, C.I. acid blue 15, C.I. acid blue 59, C.I. acid blue 23, C.I. acid blue 249, C.I. acid black 2, and C.I. food black 2.

Examples of direct dyes are: C.I. direct yellow 33, C.I. direct yellow 44, C.I. direct yellow 50, C.I. direct yellow 86, C.I. direct yellow 144, C.I. direct orange 26, C.I. direct orange 102, C.I. direct red 4, C.I. direct red 95, C.I. direct red 242, C.I. direct red 9, C.I. direct red 17, C.I. direct red 28, C.I. direct red 81, C.I. direct red 83, C.I. direct red 89, C.I.

direct red 225, C.I. direct red 227, C.I. direct blue 15, C.I. direct blue 76, C.I. direct blue 85, C.I. direct blue 200, C.I. direct blue 201, C.I. direct blue 202, C.I. direct black 19, C.I. direct black 22, C.I. direct black 31, C.I. direct black 51, and C.I. direct black 154. /463

Examples of reactive dyes are: C.I. reactive yellow 17, C.I. reactive red 6, and C.I. reactive blue 2.

In addition, the high-tone dyes below can also be effectively used in the present invention as magenta dyes:

(Where Q denotes a benzene ring containing a lower alkyl group, sulfone group, carboxyl group, or halogen; R^{22} denotes hydrogen or a lower alkyl group, M^+ denotes Li^+ , Ne^+ , K^+ , or N^+ ,

and Y denotes

(where R^{21} denotes hydrogen, a lower alkyl group, a lower alkoxy group, a hydroxyl group, or a halogen), or

In most ink-jet recording methods, only a limited group of dyes can be used to achieve water-resistant images. That is, direct dyes are normally used to achieve water resistance. However, since water resistance is heightened by the use of an organic cationic compound in the method of the present invention, dyes such as acid dyes of high solubility which tend not to clog the nozzles and dyes with better color tone can be employed. Furthermore, in contrast to the usual ink-jet recording methods, since water resistance improves the greater the number of anionic groups per dye molecule in the method of the present invention, the greater the number of anionic groups the higher the solubility imparted to the dye. Thus, dyes suitable for use in the method of the present invention are not limited to those recorded in the above-mentioned color index.

The proportion in the ink of these pigments is 0.2-20 weight percent, preferably 0.5-7 weight percent.

Ink is prepared by dissolving the dyes in a solvent such as water or an organic solvent (an alcohol such as methanol or ethanol, a ketone such as acetone or methyl ethyl ketone, or the like). The use of water is preferable when the solubility and stability of the dye in these solvents is taken into consideration.

As mentioned above, the drying property of the ink improves when a penetrant is added to the organic cationic compound-containing solution. However, to further improve the drying property of the ink, a penetrant is added to the ink. An ink

surface tension of 50 dyne/cm or less is particularly desirable. The same penetrants that are added to the organic cationic compound-containing solution can be employed to the ink as needed. The proportion of penetrants added to the ink must be chosen so that the surface tension does not drop so low as to preclude printing, blurring of the image does not occur, and dot spreading does not become excessive. Thus, penetrants are desirably added to produce a surface tension within the range of 30-50 dyne/cm.

In addition, other additives blended into the ink in normal ink-jet recording methods can also be added to the ink in the method of the present invention. Examples are the polyhydric alcohol penetrants, viscosity-adjusting agents, preservatives, pH-adjusting agents, and the like recorded in the description of the organic cationic compound-containing solution set forth above.

The recording medium is not specifically limited. /464 [illegible]. Examples of recording media are: commercially available sized paper; medium quality paper; Japanese paper; fibers such as cotton, acetate, and nylon, or fabrics of such fibers; and films of plastics such as polyester and polycarbonate coated on the surface of a hydrophobic polymeric compound such as polyvinyl alcohol or polyvinyl pyrrolidone. From the viewpoint of drying properties, it is particularly preferable in the method of the present invention to print on sized paper and fabrics.

An organic cationic compound-containing solution (the

colorless or light-colored liquid containing the organic cationic compound), ink (containing dyes having anionic groups), and a recording medium are employed in the ink-jet recording method of the present invention. First, prior to printing with ink (preferably immediately prior), the organic cationic compound-containing solution is adhered to the recording medium. Then, without any particular forced drying of the recording medium by heating or the like, the ink is adhered to the portion on which the organic cationic compound-containing solution has been adhered to bond the anionic groups in the dye to the anionic groups in the organic cationic compound, forming in the solvent an insoluble or little-soluble salt which appears as the image.

There are a number of methods of adhering the organic cationic compound-containing solution to the recording medium. In one method, the organic cationic compound-containing solution is adhered over the entire surface of the recording medium by spraying and the use of rollers. After the organic cationic compound-containing solution has soaked the recording medium, surplus organic cationic compound-containing solution is removed with a squeeze roller or the like. However, the task is preferably accomplished by an ink-jet system in which organic cationic compound-containing solution is selectively and uniformly applied only to portions where ink will be later adhered.

However, when applying organic cationic compound-containing solution by this ink-jet system, if the diameter of a single dot

formed on the recording medium by one drop of organic cationic compound-containing solution is made roughly equal to the diameter of a dot made by a single drop of ink, when selectively adhering organic cationic compound-containing solution, the positions at which organic cationic compound-containing solution is adhered and those at which ink is adhered must match precisely, making it difficult to adjust the spraying positions of the two liquids. Thus, it is desirable to make the diameter of the dot of organic cationic compound-containing solution on the recording medium larger than the diameter of the dot of ink. This is preferably accomplished by (a) making the diameter of the nozzle spraying organic cationic compound-containing solution larger than the diameter of the nozzle spraying ink; (b) making the viscosity of the organic cationic compound-containing solution lower than that of the ink so that when both organic cationic compound-containing solution and ink are sprayed under the same conditions, the organic cationic compound-containing solution dots have larger diameters than those of ink dots; or (c) by processing the print signal when it is difficult to achieve a difference in dot size between the organic cationic compound-containing solution and the ink so that a larger portion of organic cationic compound-containing solution is adhered around, for example, a single picture dot than is printed with ink.

One reason why the organic cationic compound-containing solution must be colorless or light-colored is that, as set forth

above, organic cationic compound-containing solution is adhered around the picture formed by adherence of ink. Another is to render the printed (formed) image almost identical to the image that would be printed by ink alone. Thus, to avoid problems in these regards, the organic cationic compound-containing solution must be substantially colorless or have little color. That is, so long as adherence of organic cationic compound-containing solution around the image cannot be [illegible], particularly when printing color images, the organic cationic compound- /465 containing solution can be either colorless or light-colored to a degree that does not affect color reproduction.

The period from the time the organic cationic compound-containing solution is adhered to the recording medium until the ink is adhered is an important factor affecting print quality (image quality). This period is appropriately determined by factors such as the quantities of organic cationic compound-containing solution and ink droplets, the flying speed of the droplets, the penetration rate of the organic cationic compound-containing solution into the recording medium, and the surface tension of the ink. Optimally, ink droplets are adhered during the several seconds immediately after the organic cationic compound-containing solution has penetrated into the recording medium and disappeared from sight. When organic cationic compound-containing solution remains on the surface of the recording medium during adhesion of ink droplets, splashing ink dirties the edge of the image and the ink moves toward the

organic cationic compound-containing solution, tending to blur the image. By contrast, when too much time elapses after the adherence of the organic cationic compound-containing solution, the cationic groups in the organic cationic compound-containing solution and the anionic groups in the dye in the ink react sluggishly, the effect of the penetrants in the organic cationic compound-containing solution diminishes, and the ink dries slowly.

To control the state of adherence of the organic cationic compound-containing solution during the application of ink, the position of the head in the printer discharging organic cationic compound-containing solution can be adjusted relative to the position of the head discharging ink, and the amount of penetrant added to the organic cationic compound-containing solution can be adjusted.

Ink-jet systems proposed by the present inventors can be employed to adhere the organic cationic compound-containing solution and ink to the recording medium. These systems are also recorded, for example, in the Television Institute Journal, 37, (7)540 (1983), relating to proposals by Mr. Junji Maeda. Representative systems are the charge-regulating type continuous spray system, and on-demand systems such as the Kayser-type, Gould-type, bubble-jet type, and Stenme-type systems.

The method recorded in Unexamined Japanese Patent Publication No. 54-43733 is [illegible] to the present invention. However, in this method, two-liquid, hardening-type components

are reacted and fixed by combining them on glass. In addition, the ink is oil-based, and the isocyanate, epoxy groups, and the like recorded in the embodiments are substantially unstable, making them unsuitable for most printers from the perspective of nozzle clogging.

Embodiments

(Percentages based on weight)

First, six types of organic cationic compound-containing solutions and 19 types of ink (5 types of yellow ink, 7 types of magenta ink, 5 types of cyan ink, and two types of black ink) were prepared according to the blends given below.

(Organic cationic compound-containing solution P-1)

Polyallylamine	5.0%
Glycerin	10.0%
Ethylene glycol	11.0%
Diethylene glycol	20.0%
Diethylene glycol monobutyl ether	12.0%
Dehydroacetic acid soda	0.1%
Purified water	remainder

(Organic cationic compound-containing solution P-2)

Polyethyleneimine	3.0%
Glycerin	10.0%
Diethylene glycol	23.0%
Diethylene glycol monobutyl ether	5.0%
Dehydroacetic acid soda	0.1%
Purified water	remainder

(Organic cationic compound-containing solution P-3)

Prepared using a quaternary polymer (*N*-trimethylaminomethyl polystyrene: in above-listed formula (10), $m=1$, $R^7=R^8=R^9=-CH_3$) in place of the polyallylamine of above-listed P-1. /466

(Organic cationic compound-containing solution P-4)

Prepared using tetraethylenepentamine in place of the polyethyleneimine of P-2.

(Organic cationic compound-containing solution P-5)

Polydimethyldiallylammonium hydrochloride	4.0%
Glycerin	10.0%
Ethylene glycol	11.0%
Diethylene glycol	32.0%
Dehydroacetic acid soda	0.1%
Purified water	remainder

(Adjusted to pH 13.5 with NaOH.)

(Organic cationic compound-containing solution P-6)

Polyallylamine	4.0%
Glycerin	5.0%
Diethylene glycol	25.0%
Propylene glycol monobutyl ether	1.0%
Purified water	remainder

(Adjusted to pH 13.5 with $(C_2H_6)_4NOH$.)

(Yellow Ink Y-1)

C.I. acid yellow 23	3.0%
Glycerin	10.0%
Ethylene glycol	15.0%

Diethylene glycol	24.0%
Diethylene glycol monobutyl ether	4.0%
Dehydroacetic acid soda	0.3%
Purified water	remainder

(Yellow Ink Y-2)

C.I. food yellow 3	3.0%
Glycerin	10.0%
Ethylene glycol	15.0%
Diethylene glycol	25.0%
Propylene glycol monobutyl ether	2.0%
Dehydroacetic acid soda	0.3%
Purified water	remainder

(Yellow Ink Y-3)

Prepared using C.I. direct yellow 142 in place of C.I. acid yellow 23 in above-listed Ink Y-1.

(Yellow Ink Y-4)

C.I. acid yellow 17	3.0%
Glycerin	10.0%
Ethylene glycol	15.0%
Diethylene glycol	28.0%
Dehydroacetic acid soda	0.3%
Purified water	remainder

(Yellow Ink Y-5)

C.I. acid yellow 23	3.0%
Glycerin	5.0%
Diethylene glycol	22.0%

Diethylene glycol monobutyl ether	3.0%
Sodium 2-pyridinethiol-1-oxide	0.2%
Purified water	remainder

(Magenta Ink M-1)

Prepared using C.I. acid red 92 in place of C.I. acid yellow 23 in above-listed Ink Y-1.

(Magenta Ink M-2)

Prepared using C.I. acid red 254 in place of C.I. food yellow 3 in above-listed Ink Y-2.

(Magenta Ink M-3)

Prepared using C.I. acid red 35 in place of C.I. acid yellow 23 in above-listed Ink Y-1.

(Magenta Ink M-4)

Prepared using a dye of structural formula (A), given below, in place of C.I. food yellow 3 in above-listed Ink Y-2.

... (A)

(Magenta Ink M-5)

Prepared using a dye of structural formula (B), given below, in place of C.I. acid yellow 23 in above-listed Ink Y-1. /467

... (B)

(Magenta Ink M-6)

Prepared using C.I. acid red 35 in place of C.I. acid yellow 17 in above-listed Ink Y-4.

(Magenta Ink M-7)

Prepared using the above-listed dye of structural formula (A) in place of C.I. acid yellow 23 in above-listed Ink Y-5.

(Cyan Ink C-1)

Prepared using C.I. direct blue 86 in place of C.I. acid yellow 23 in above-listed Ink Y-1.

(Cyan Ink C-2)

Prepared using C.I. direct blue 9 in place of C.I. acid yellow 23 in above-listed Ink Y-1.

(Cyan Ink C-3)

Prepared using C.I. direct blue 86 in place of C.I. food yellow 3 in above-listed Ink Y-2.

(Cyan Ink C-4)

Prepared using C.I. direct blue 86 in place of C.I. acid yellow 17 in above-listed Ink Y-4.

(Cyan Ink C-5)

Prepared using C.I. direct blue 249 in place of C.I. acid yellow 23 in above-listed Ink Y-5.

(Black Ink Bl-1)

Prepared using C.I. food black 2 in place of C.I. acid yellow 23 in above-listed Ink Y-1.

(Black Ink Bl-2)

Prepared using C.I. acid black 72 in place of C.I. acid

yellow 23 in above-listed Ink Y-5.

In addition to the above, one type of organic cationic compound-containing solution (Q-1) and four types of ink (Yellow Ink Y', Magenta Ink M', Cyan Ink C', and Black Ink Bl') were separately prepared.

(Organic cationic compound-containing solution Q-1)

Polyallylamine	4.0%
Glycerin	10.0%
Ethylene glycol	11.0%
Diethylene glycol	32.0%
Purified water	43.0%

(Adjusted to pH 8.0 with NaOH)

(Yellow Ink Y')

C.I. acid yellow 23	3.0%
Glycerin	10.0%
Ethylene glycol	15.0%
Diethylene glycol	14.0%
Diethylene glycol monobutyl ether	14.0%
Dehydroacetic acid soda	0.3%
Purified water	remainder

(Ink Y' is above-listed Ink Y-1 with an increased amount of diethylene glycol monobutyl ether.)

(Magenta Ink M')

Prepared using C.I. acid red 92 in place of the C.I. acid yellow 23 in above-listed Ink Y'.

(Cyan Ink C')

Prepared using C.I. direct blue 85 in place of the C.I. acid yellow 23 in above-listed Ink Y'.

(Black Ink Bl')

Prepared using C.I. food black 2 in place of the C.I. acid yellow 23 in above-listed Ink Y'.

These organic cationic compound-containing solutions and inks were used to print on commercial high-quality paper with either a Kayser on-demand ink-jet printer or a charge-regulating type ink-jet printer, as shown in Table 1. /468

Table 1

No.	Method of Printing	Organic Cationic Compound-Containing Solution	Ink			
			Yellow w	Magenta a	Cyan	Black
1	o	P-1	Y-1	M-1	C-1	Bl-1
2	o	P-2	Y-2	M-2	C-3	Bl-1
3	o	P-3	Y-3	M-3	C-2	Bl-1
4	o	P-4	Y-4	M-6	C-4	Bl-1
5	o	P-5	Y-2	M-2	C-2	Bl-1
6	o	P-1	Y-3	M-4	C-2	Bl-1
7	o	P-3	-	M-5	-	-
8	C	P-6	Y-5	M-7	C-5	Bl-2
9	o	None	Y-1	M-1	C-1	Bl-1
10	C	None	Y-5	M-7	C-5	Bl-2
11	o	Q-1	Y-1	M-1	C-1	Bl-1
12	o	None	Y'	M'	C'	Bl'
13	o	Q-1	Y-4	M-6	C-4	-
14	o	Q-1	-	M-5	C-4	-

Note 1: In the Method of Printing column, ' denotes an on-demand

system, C denotes a charge-regulated system. The printers were approximately as follows.

(1) Kayser-Type On-Demand Ink-Jet Printer

Nozzle and ink chamber 60 μm in diameter, equipped with 5 heads each having 9 driven elements, used to spray organic cationic compound-containing solution, yellow ink, magenta ink, cyan ink, and black ink, respectively. Fig. 1 shows a plan view of the printer carriage portion. Fig. 2 shows a side view of the carriage portion. Fig. 3 shows a front view of a (single) head. A carriage 1 is scanned (in the direction indicated by the arrow in Fig. 1) along a shuttle 2 and organic cationic compound-containing solution is fed to head member 31P from an organic cationic compound-containing solution cartridge 3P provided on carriage 1. Ink is fed from ink cartridges 3Y, 3M, 3C, and 3B1 to heads 31Y, 31M, 31C, and 31B1, respectively. Voltage is applied on the basis of an image signal to electrostrictive elements (not shown) mounted on the heads to form an image on recording paper 4 (the recording medium). In the figure, 5 denotes a platen.

Head 31P, used to spray organic cationic compound-containing solution, is mounted below carriage 1 ink heads 31y, 31m, 31c, and 31b. Since recording medium 4 is scanned from above, the design is such that the organic cationic compound-containing solution is adhered before the ink to recording medium 4. The organic cationic compound-

containing solution corresponds to the images of all the printed portions of yellow, magenta, cyan, and black images, and the signal is processed so that only one dot of excess is discharged around the image. Fig. 4 shows adherence of ink on the adhered portion of organic cationic compound-containing solution and the formation of the image (I).

(2) Charge-Regulated Ink-Jet Printer

Printing was conducted with the printer shown in Fig. 6, equipped with five of the binary charge-regulated type ink-jet units shown in Fig. 5. The print heads for each of the inks were positioned within carriage 1 as indicated in Fig. 7. Nozzles having diameters of 25 μm were employed. The [illegible] frequency was 132 KHz.

Note 2: Nos. 11, 13, and 14 are reference examples, and Nos. 9, 10, and 12 are comparative examples. In No. 14, M-6 or C-[illegible] ink was first loaded into the organic cationic compound-containing solution head, Q-1 solution was loaded into the yellow head, and printing was conducted (after printing with ink, a liquid containing a water-resistant agent was adhered).

The printing results are as shown in Table 2.

/469

Table 2

[#T]	Image density
[#U]	Water resistance
[#V]	Drying time (sec)
[#W]	(Black excluded)
[#X]	Image blurring
[#Y]	Color tone
[#Z]	Image definition
[#A1]	Ink surface tension
[#B1]	42-44 (Excluding black)

[#C1] 52-57 (Excluding black)

Note 1: Y denotes a yellow image, M a magenta image, C a cyan image, and Bl (black) a black image.

Note 2: The picture density was determined by measuring a solid portion with a MacBeth densitometer.

Note 3: The water resistance of the image was obtained by immersing an image sample in 30°C water for 1 min, measuring the image density before and after immersion with a MacBeth densitometer, and determining the amount of color fading in the formula below:

$$1 - \frac{(\text{main color density before immersion})}{(\text{main color density after immersion})} \times 100 (\%)$$

Note 4: The drying time was determined as the time elapsing after printing until ink would not transfer to filter paper.

Note 5: Image blurring was evaluated by visually determining the presence or absence of feathering. An "X" indicates that feathering was present; a "O" indicates there was no feathering.

Note 6: Color tone was evaluated visually. Here, a "O" indicates that the adherence of the organic cationic compound-containing solution was noticeable [sic: unnoticeable] or almost unnoticeable, and when absent, no significant difference in color tone was present. Any clear difference from this was denoted by an "X".

Note 7: Image definition was visually evaluated as the presence or absence of ink outflow from the edge of a solid

portion of image having two overlapping colors. The presence of outflow was denoted by an "X" and its absence by a "O."

Note 8: Nozzle clogging was tested by printing, allowing the nozzle to remain at 20°C and 65% RH for 2 months under the same conditions as when printing was stopped, and then determining whether or not normal printing was again possible. A "O" indicates no clogging and an "X" indicates clogging.

Note 9: The shelf life was determined by charging ink and organic cationic compound-containing solution to polyethylene containers; storing them for three months at -20°C, 4°C, 20°C, 50°C, and 70°C, respectively; and observing before and after storage the change in viscosity, surface tension, and electrical conductivity and the presence or absence of precipitates. A "O" indicates good shelf life and an "X" poor shelf life.

Effects

The following effects are achieved by the ink-jet recording method of the present invention:

- (a) The dye in the ink and the cationic groups in the organic cationic compound-containing solution bond, the dye is bonded through the medium of the organic cationic compound, and a water-insoluble aggregate is formed, substantially increasing the water resistance of the image.
- (b) Since the dye forms an aggregate, the dye does not penetrate

into the interior of the paper but stops near the surface of the paper, improving the definition and density of the image. Since the solvent only penetrates the surface of the paper, the dye does not spread. Thus, an image with good sharpness and of high resolution is obtained.

- (c) Since the dye forms an aggregate, it is possible to suppress penetration of the color material into the paper surface. Thus, no image blurring occurs even when using readily drying inks with low surface tensions, and drying properties are accordingly better. /470
- (d) Improved drying properties are achieved even when using a high surface tension ink due to penetrants in the organic cationic compound-containing solution.
- (e) The resistance to light of the aggregate of dye and organic cationic compound is better than when the dye does not form an aggregate (the reason is not clear).
- (f) Since the dye employed in the ink can be selected irrespective of water resistance, it is possible to improve both resistance to clogging and color tone.

4. Brief Description of the Figures

Fig. 1 is a plan view of the carriage portion of a Kayser-type on-demand ink-jet printer. Fig. 2 is a side view of the same. Fig. 3 is the front view of an ink head.

Fig. 4 is a drawing showing the shape of an image formed (printed) on a recording medium.

Fig. 5 is a drawing showing a schematic of a binary charge-regulated ink[-jet] unit. Fig. 6 is a drawing showing how printing is effected by a printer employing the unit of Fig. 5.

Fig. 7 is a drawing showing the positioning of print heads.

1=Carriage

2=Shuttle (carriage guide)

21=Carriage feed screw

3P=Organic cationic compound-containing solution cartridge

3Y=Yellow ink cartridge

3M=Magenta ink cartridge

3C=Cyan ink cartridge

3Bl=Black ink cartridge

31=Head

31P=Organic cationic compound-containing solution head

31Y=Yellow ink head

31M=Magenta ink head

31C=Cyan ink head

31Bl=Black ink head

4=Recording medium

5=Platen (drum)

6=Ink pump unit

71=Charging electrode

72=Deflecting electrode

8=Garter [spring]

Fig. 1

[(#top) Paper surface]

Fig. 2

Fig. 3

Fig. 4

Fig. 5

/471

Fig. 6

Fig. 7

1. Black unit

2. Cyan unit

3. Magenta unit

4. Yellow unit

Organic cationic compound-containing solution unit

⑩ 日本国特許庁(JP)

⑪ 特許出願公開

⑫ 公開特許公報(A)

昭63-299971

⑬ Int. Cl.⁴

識別記号

庁内整理番号

⑭ 公開 昭和63年(1988)12月7日

B 41 M 5/00
B 41 J 3/04

1 0 1

A--7915-2H
Z-8302-2C
Y-8302-2C
Z-7513-2C
E-7915-2H
8721-4J

B 41 M 5/00
C 09 D 11/00

P S Z
1 0 1

審査請求 未請求 発明の数 1 (全15頁)

⑮ 発明の名称 インクジェット記録方法

⑯ 特 願 昭62-133442

⑰ 出 願 昭62(1987)5月30日

⑱ 発 明 者 有 賀 保
⑱ 発 明 者 村 上 格 二
⑱ 発 明 者 島 田 勝
⑱ 発 明 者 永 井 希 世 文
⑱ 発 明 者 上 村 浩 之
⑲ 出 願 人 株 式 会 社 リ コ ー
⑳ 代 理 人 弁 理 士 佐 田 守 雄

東京都大田区中馬込1丁目3番6号 株式会社リコー内
東京都大田区中馬込1丁目3番6号 株式会社リコー内
東京都大田区中馬込1丁目3番6号 株式会社リコー内
東京都大田区中馬込1丁目3番6号 株式会社リコー内
東京都大田区中馬込1丁目3番6号 株式会社リコー内
東京都大田区中馬込1丁目3番6号 株式会社リコー内
東京都大田区中馬込1丁目3番6号 外1名

明 細 書

1. 発明の名称

インクジェット記録方法

2. 特許請求の範囲

- 記録媒体上に1分子当り2個以上のカチオン性基を有する有機化合物を含有する顔色又は淡色の液体を付着した後、その液体の付着部分に、アニオン染料を含有するインクを付着させて画像を形成せしめることを特徴とするインクジェット記録方法。
- 前記顔色又は淡色の液体が浸透剤を含んでいる特許請求の範囲第1項記載の記録方法。
- 前記浸透剤がノニオン系界面活性剤、陰イオン系界面活性剤、陽イオン系界面活性剤及び非离子系界面活性剤からなる群より選ばれた少なくとも1種である特許請求の範囲第2項記載の記録方法。
- 前記顔色又は淡色の液体が多量アルコールを含んでいる特許請求の範囲第1項記載の記録方法。

5. 前記顔色又は淡色の液体がpH5-14以上である特許請求の範囲第1項記載の記録方法。

6. 前記インクの表面張力が50dyne/cm以下である特許請求の範囲第1項記載の記録方法。

7. 前記アニオン染料は分子中に-SO₃⁻、-COO⁻又は-O⁻の酸性基を有するものである特許請求の範囲第1項記載の記録方法。

3. 発明の詳細な説明

(技術分野)

本発明はインクジェット記録方法に関し、詳しくは、ノズルからのインクの噴射に先立って記録媒体上にそのインクを良好に定着させるための顔色又は淡色の液体を付着させるようにしたインクジェット記録方法に関する。

(従来技術)

インクジェット記録方法は(イ)高速記録が可能である、(ロ)記録媒体に非接触であるため記録媒体には摩擦等をはじめ種々のものが使用可能である、(ハ)カラー記録が可能である、等の利点を有していることから近時

S.T.I.C. Translations Branch

PTO 97-4405

大いに活用されている。

その一方で、このインクジェット記録方法はノズルの目詰りという問題が懸念されている。これを解決するには、ノズル先端部の形状、構造に工夫を加えることの外に、染料として染料に対し溶解性の高いものがインクに採用されることが必要とされている。だが、一般に溶解性の高い染料をインクに使用すると得られた画像の耐久性（染料が水の場合は耐水性）が低くなる傾向がある。

こうした欠陥を解消する手段として(1)記録紙に染料を定着するための材料をあらかじめ塗工しておく（特開昭56-86789号、特開昭55-144172号、特開昭56-84982号などの公報に記載）、(2)印字した画像に染料とレーキを形成する耐水化剤を付与する（特開昭55-150386号公報に記載）等が提案されている。しかし、前記(1)の方法では記録媒体として特定の記録紙を用いる必要がある。前記(2)の方法では耐水性の問題は解決されるものの、

印字後の画像の乾燥性、画像の解像性、画像濃度などに対してはまったく又は僅かしか効果がないため、記録紙として活用されるものは可成り制限されてしまう。

また、これまでのインクジェット記録方法で使用されているインクによって一般のオフィスで使用されている記録用紙（記録媒体）に印字すると乾燥時間が遅く、記録用紙供給系でのオフセットによる地汚れや、スミアが発生したり、特にカラー記録の場合には記録用紙（記録媒体）の単位面積当りに付与させるインク量が多い（多色の重ねになることによる）ため、インクが不要の部分に流れ出して画像がにじんでしまう欠点がある。

かかる乾燥性の問題を解決するための手段として(3)サイズ剤を添加しないか又はその添加量を少なくした紙を記録媒体として使用する（特開昭52-74340号公報に記載）、(4)表面に白色顔料又は水溶性高分子材料を主成分としたコート層を設けた紙を記録媒体とし

て使用する（特開昭52-53012号、特開昭56-89594号などの公報に記載）、(5)インク中に界面活性剤等インクの浸透性を高めるための化合物を添加してインクの表面張力を低下せしめる（特開昭55-65269号公報に記載）、(6)本来的に表面張力の低いアルコール、ケトン等の有機溶媒を主体とするインクを用いる、(7)揮発性の溶媒を主体としたインクを用いる（特開昭55-86876号公報に記載）、(8)インクを希釈使用する、等が提案されている。しかし、前記(3)(4)の方法では、前記(1)と同様、特定の記録媒体を用いる必要がある。前記(5)(6)の方法では乾燥性は確かに高まるものの、インクの媒体（キャリア）とともにインク中の染料も記録画像中に相対浸み込んでしまうため、染料が記録用紙の奥深くまで浸透しやすく、画像濃度が低下したり、画像の鮮明性が低下しやすいなどの不都合がみられる。また、記録表面に対する耐水性が向上するためフェザリングが発生したり、解像

力が低下する（表面方向にインクが染みがリドット後が大きくなる）などの不都合もみられる。前記(7)の方法では記録用紙へのインクの浸透が速まりそれと同時に記録用紙表面からの溶媒の蒸発も生じやすく速乾性は充足されるが、前記(6)と同様な不都合が認められるのに加えて、ノズル部での溶媒の蒸発による目詰りが生じやすい。前記(8)の方法ではインクの希釈により溶媒が蒸発してインク組成が変化し印字操作が不協となったり、インク組成の変化を補償するための機構が複雑になるという欠陥をもち併せている。

更に、印字画像のシャープネスを向上する手段として(9)記録媒体上にあらかじめカルボキシメチルセルロース、ポリビニルアルコール、ポリ酢酸ビニル等のポリマーの溶液を塗布してから印字する方法が提案されている（特開昭56-89595号公報に記載）。この(9)の方法によればシャープネスの向上効果は得られるが、ポリマー溶液が高粘度であるためそ

の溶媒自体の乾燥性が悪く、加えて印字したインクの乾燥性も通常の紙に印字した場合に比較して改善効果があり認められないという欠点がある。

こうした実情を反映して、上記のごとき欠陥の生じないインクジェット記録方法の改善が望まれている。

(目 的)

本発明はかかる要望にそったもので、印字後の画像の乾燥性、耐水性、耐光性、解像度、鮮明性、シャープネスなどを向上させ、更にその印字後の画像温度を高めるとともにノズルの目詰りを防止し、プリンターの信頼性を高めるようにしたインクジェット記録方法を提供するものである。

(構 成)

本発明のインクジェット記録方法は、記録媒体上に1分子当り2個以上のカチオン性基を有する有機化合物を含有する無色又は淡色の液体を付着した後、その液体の付着部分に、

アニオン染料を含有するインクを付着させて画像を形成せしめることを特徴としている。



ちなみに、本発明者らは、記録媒体へのインクの付着に先立って、1分子当り2個以上のカチオン性基を有する有機化合物を含有する無色又は淡色の液体（以降「有機カチオン性化合物含有溶液」と称することがある）を記録媒体に付着させ、続いて、その有機カチオン性化合物含有溶液の付着されたところに、アニオン染料を含有したインクを塗布状に供給するようにすれば、前記カチオン性化合物におけるカチオン性基と前記染料中のアニオン性基とが結合して溶媒に不溶又は難溶の塩から形成される画像が得られることを確めた。本発明はそれに基づいてなされたものである。





以下に本発明方法をさらに詳細に説明する。

前述のとおり、本発明のインクジェット記録方法においては、まず記録媒体上に有機カチオン性化合物を含有する無色又は淡色の液体が付着される。

この有機カチオン性化合物における代表例としては(a)第一級、第二級、第三級及び第四級の窒素（アミン又はアンモニウム）、リン（ホスホニウム）を分子鎖中あるいはペンダント基として有する高分子化合物、(b)低分子量のカチオン性有機化合物がある。

前記(A)の具体例としては次のようなものがあげられる。





これらの高分子カチオン性化合物は塩酸塩、酢酸塩、硝酸塩、硫酸塩等の任意の酸との化合物として用いることができる。

上記の高分子カチオン性有機化合物の商品名としては、サンフィックス414、414-C555、555US、70、PRO-100(以上三洋化成社製)、プロテックス260、フィックスR、H、SK、MCL、FM(以上星田加工社製)、モーリンフィックスコンク3M(モーリン化学社製)、アミゲン(第一薬品工業社製)、エボミンP100(日本触媒社製)、フィックスオイルR737、E50(以上明成化学社製)、ネオフィックスRS(日理化学社製)、ポリアミンスルホン(日東紡績社製)、ポリフィックス501(昭和高分社製)、ニカフィックスD100(日本カーバイド社製)、レボゲンB(バイエル社製)、カイメン557(ディック・ハーキュレス社製)等が挙げられる。

なお、これらの高分子カチオン性化合物はあまり分子量が大きいと、溶解性が悪くなる。

溶液の粘度が高くなり過ぎるという問題が生じるから、本発明方法では好ましくは分子量10万以下のものが用いられる。特に好ましくは前記のカチオン性基を1分子中に5~200個含む分子量20000以下の化合物である。

上記(B)の具体例としては次のものがあげられる。

エチレンジアミン、ヘキサメチレンテトラミン、ピペラジン、1-(2'-アミノエチル)ピペリジン、1-(2'-アミノエチル)アジリジン、1-(2'-アミノエチル)ピロリジン、1-(2'-アミノエチル)ヘキサメチレンジアミン、ヘキサメチレンジアミン、ジエチレントリアミン、トリエチレンテトラミン、テトラエチレンペンタミン、N、N'-ビス-(3-アミノプロピル)ブトレッシン、N-(3-アミノプロピル)ブトレッシン、1,4-ジアザシクロヘプタン、1,5-ジアザシクロオクタタン、1,4,11,14-テトラアザシクロエイコサン、1,10-ジアザシクロオクタデカン、1,2-ジアミノプロパ

ン-3-オール、1-アミノ-2,2-ビス(アミノニチル)プロパン-1-オール、1,3-ジアミノプロパン-2-オール、N-(2-オキシプロピル)エチレンジアミン、ヘプタエチレンオクタミン、ノナエチレンデカミン、1,3-ビス(2'-アミノエチルアミノ)プロパン、トリエチレン-ビス(トリメチレン)ヘキサミン、1,2-ビス-(3'-(2'-アミノエチルアミノ)プロピルアミン)エタン、ビス(3-アミノエチル)アミン、1,3-ビス(3'-アミノプロピルアミノ)プロパン、syn-ホモスベルミジン等の脂肪族又は脂環式の多価アミン類であり、これらの中でも1分子中に3個以上の窒素原子を有する化合物が本発明方法では特に好ましく用いられる。これは2個以下の窒素原子しかない化合物では原料と反応して不溶性の結合体を形成しにくいためである。また、フェニレンジアミン、トリアミノベンゼン、テトラアミノベンゼン、ペンタアミノベンゼン、ヘキサアミノベンゼン、2,6-又は2,5-ジアミノ-p

-ベンゾキノンジイミン、2,3,7,8-テトラフ
ミノフェナジン等の芳香族多価アミノ酸も用
いられてよい。

これら化合物の合成法については、BARTON,
OLLIS "COMPREHENSIVE ORGANIC CHEMISTRY"
Perryson Press (1979)等に記載されている。

こうした有機カチオン性化合物の顔色又は
顔色の液体中の含有量に特に制限はないが、
後から付与されるインクの染料のアニオン性
基に対して1/10~100当量好ましくは1/2~10
当量が単位面積の記録媒体に付与されるよう
な濃度で用いることが好適である。

有機カチオン性化合物含有溶液は、これが
記録媒体に付与された後には速かに乾燥する
ことが特に高速で印字をする場合に要求され
る。また、印字されたインクも速かに浸透す
ることが要求される。この要求を満たさせる
ために透明な液体(有機カチオン性化合物含
有溶液)自体および/又はインクの記録媒体
への浸透性を高めるための化合物を有機カチ

オン性化合物含有溶液に添加することが望ま
しい。

この浸透性を高めるための化合物(浸透剤)
の例としては、ポリオキシエチレンアルキル
エーテル類、ポリオキシエチレンアルキルフ
ェニルエーテル類、ポリオキシエチレンアル
キルエステル類、ポリオキシエチレンアルキ
ルソルビタンエステル類、ポリオキシエチレ
ンアルキルアミン類、グリセリン脂肪酸エス
テル類、ソルビタン脂肪酸エステル類、プロ
ピレングリコール脂肪酸エステル類、ポリオ
キシエチレングリコール脂肪酸エステル類等
のノニオン系界面活性剤；アルキル硫酸塩類、
ポリオキシエチレンアルキルエーテル硫酸塩
類、ポリオキシエチレンアルキルエーテル硫
酸塩類、アルキルベンゼンスルホン酸塩類、
N-アシルアミノ酸塩類、アルキルスルホコ
ハク酸塩類、アルキルリン酸塩類等の陰イオ
ン系界面活性剤；ベンザルコニウム塩類など
の陽イオンアミン類等の陽イオン系界面活性剤；

パーフルオロアルキルリン酸エステル類、パー
フルオロアルキルカルボン酸塩類、パーフ
ルオロアルキルペグ^①イン類等のフッ素系界面
活性剤などがあげられる。

これらの中でより具体的に好ましい浸透剤
は、ジエチレングリコールモノブチルエーテ
ル、ジエチレングリコールモノフェニルエー
テル、プロピレングリコールモノブチルエー
テル、フッ素系界面活性剤であり、これらは
浸透性を高める効果が大きい。

有機カチオン性化合物含有溶液中へのこれ
ら浸透剤の添加量は、使用される浸透剤の類
類により幾分異なるが30重量%以下、好まし
くは0.001~30重量%より好ましくは0.1~15
重量%くらいが適宜である。

この他に、有機カチオン性化合物含有溶液
に添加しうるものとしては、通常のインクジ
ェット記録方法に用いられるインクに必要よ
り添加されるものが同様に使用できる。例え
ば、粘着調整剤、防腐剤(防食防錆剤を含む)、

pH調整剤、紫外線吸収剤などがある。

粘着調整剤としては、多価アルコールの使
用がノズル部の目詰り防止効果をもち併せて
いることから特に望ましい。多価アルコール
の例としてエチレングリコール、ジエチレン
グリコール、トリエチレングリコール、テト
ラエチレングリコール、ポリエチレングリコ
ール、プロピレングリコール、ジプロピレン
グリコール、グリセリン、ジエタノールアミ
ン、トリエタノールアミン等が挙げられる。
これらの多価アルコールの添加量は0~70重
量%が適当であり特に好ましくは5~35重量
%である。多価アルコール以外の粘着調整剤
としては、ジエチレングリコールモノメチル
エーテル、ジエチレングリコールモノエチル
エーテル、トリエチレングリコールモノメチ
ルエーテル等の多価アルコールのアルキルエ
ーテル類、多価アルコールのエステル類、N
-メチル-2-ピロリドン、1,3-ジメチルイミダ
ゾリジノン等の窒素系水溶性化合物等があげ

られる。これら腐食阻害剤は陽イオン性化合物を良く溶解することのできるものが望ましいことから特にエチレングリコール、ジエチレングリコール、グリセリンの使用が有利である。

防食剤としてはデヒドロキシ安息香酸、ソルビン酸、安息香酸、ペンタクロロフェノールナトリウム、2-ピリジンチオール-1-オキシドナトリウム、2,4-ジメチル-6-アセトキシ-m-ジオキサン、1,2-ベンズチアゾリン-3-オン等の化合物をあげることができる。

印刷液剤には水酸化ナトリウム、水酸化カリウム等の水酸化アルカリ金属塩、炭酸ナトリウム、炭酸カリウム等の炭酸アルカリ塩、水酸化アンモニウム、水酸化第四級アンモニウム、ジエタノールアミン、トリエタノールアミン等が用いられる。更にpHの調整性を高めるためにリン酸ナトリウム、シウ酸ナトリウムのような塩基を添加することができる。有機カチオン性化合物含有溶液のpH値は、用

いた有機カチオン性化合物が比喩を生じないこと、有機カチオン性化合物含有溶液がそれに浸する部材を浸さないこと等を考慮して決められるべきであり、システムを構成する部材、用いる有機カチオン性化合物により適当なpH値を選択しなければならない。従って、有機カチオン性化合物含有溶液のpH値は5~14好ましくは12以上が適当である。pH=12以上にすることにより、有機カチオン性化合物含有溶液の記録媒体への吸収速度及び後に付着されるインクの吸収速度が速くなり有利である。

次にアニオン性基を有する染料を含有するインクについて述べると、ここでの染料は有機カチオン性化合物の陰イオンと結合して結晶に不溶又は懸濁の態を形成するものであればよく、特に分子中に $-SO_3^-$ 、 $-COO^-$ 、 $-O^-$ のアニオン性基を有する染料が用いられる。カラーインデックの分類に従えば、酸性染料、反応性染料、直接染料がこれらの酸性基を有

するものである。

具体的な染料の例としては、次のものを挙げる事が出来る。


酸性染料としてはC.I.アシッド・イエロー17, C.I.アシッド・イエロー23, C.I.アシッド・イエロー42, C.I.アシッド・イエロー44, C.I.アシッド・イエロー79, C.I.アシッド・イエロー142, C.I.アシッド・レッド35, C.I.アシッド・レッド42, C.I.アシッド・レッド52, C.I.アシッド・レッド81, C.I.アシッド・レッド87, C.I.アシッド・レッド92, C.I.アシッド・レッド134, C.I.アシッド・レッド242, C.I.アシッド・レッド254, C.I.アシッド・レッド289, C.I.アシッド・ブルー1, C.I.アシッド・ブルー9, C.I.アシッド・ブルー15, C.I.アシッド・ブルー59, C.I.アシッド・ブルー93, C.I.アシッド・ブルー248, C.I.アシッド・ブラック2, C.I.フード・ブラック2などが例示できる。

直接染料としてはC.I.ダイレクト・イエロー33, C.I.ダイレクト・イエロー44, C.I.ダイレクト・イエロー50, C.I.ダイレクト・イエロー86, C.I.ダイレクト・イエロー144, C.I.ダイレクト・オレンジ26, C.I.ダイレクト・オレンジ102, C.I.ダイレクト・レッド4, C.I.ダイレクト・レッド95, C.I.ダイレクト・レッド242, C.I.ダイレクト・レッド9, C.I.ダイレクト・レッド17, C.I.ダイレクト・レッド28, C.I.ダイレクト・レッド81, C.I.ダイレクト・レッド83, C.I.ダイレクト・レッド89, C.I.ダイレクト・レッド225, C.I.ダイレクト・レッド27, C.I.ダイレクト・ブルー15, C.I.ダイレクト・ブルー78, C.I.ダイレクト・ブルー85, C.I.ダイレクト・ブルー200, C.I.ダイレクト・ブルー201, C.I.ダイレクト・ブルー202, C.I.ダイレクト・ブラック19, C.I.ダイレクト・ブラック22, C.I.ダイレクト・ブラック32, C.I.ダイレクト・ブラ

ック51、C.I.ダイレクト・ブラック154などが例示できる。

反応性染料としてはC.I.リアクティブ・イニロー17、C.I.リアクティブ・レッド6、C.I.リアクティブ・ブルー2などが例示できる。


その他、本発明においてはマゼンタ染料として高色調の下記の染料も有効に使用しうる。




(但し、Qは低級アルキル基、スルホン基、カルボキシル基、ハロゲン基を含むベンゼン環を換わす。

R¹⁰は水素又は低級アルキル基を換わす。

M⁺はLi⁺、Na⁺、K⁺又はN⁺を換わす。



(R¹¹は水素、低級アルキル基、低級アルコキシ基、水酸基又はハロゲン)又は



一般のインクジェット記録方法では得られた画像の耐水性を得るために使用できる染料が限定されてしまう。すなわち、耐水性の点からは一般には直接染料を用いることになるが、本発明方法においては、耐水性は有機カチオン性化合物により高められるので、酸性染料のように溶解性が高く目詰りを生じにくい染料、より色調の優れた染料を用いることができる。また、本発明方法においては、一

般のインクジェット記録方法とは逆に、染料1分子当りのアニオン性基の数が多く耐水性が向上するため、アニオン性基数の増加により高い溶解性を染料に与えることができる。従って、本発明方法に使用できる染料は上記のカラー・インデックスに記録されたものに限定されるものではない。

これら染料のインク中の含有量は0.2〜20重量%好ましくは0.5〜7重量%である。

インクはこれら染料を水、有機溶媒(メタノール、エタノールのごときアルコール類; アセトン、メチルエチルケトンのごときケトン類など)等の溶媒に溶解させて調製される。これら溶媒のうち染料の溶解性、安定性を配慮すると水の使用が最も好ましい。

先に述べたように、有機カチオン性化合物含有溶媒に浸透剤を加えておくようにすればインクの乾燥性は向上するが、このインクの乾燥性を一層向上せしめるためにはインク中にも浸透剤を加えて、インクの表面張力を

を50dyne/cm以下にすることが特に好ましい。浸透剤としては有機カチオン性化合物含有溶媒に必要により添加されるものと同様なものを用いることができる。インクへの浸透剤の添加量は、表面張力が低下し過ぎて印字が不能になったり、画像のにじみが生じたり、ドット径の広がりが大きくなり過ぎない範囲で選択すべきであり、従って、表面張力としては30〜50dyne/cmの範囲となる量で浸透剤が添加されるのが望ましい。

その他、通常のインクジェット記録方法でのインクに加えられているものと同様な添加物が本発明方法でのインクにも添加されてよく、これには前述の有機カチオン性化合物含有溶媒の調製で記載した多価アルコール等の凝固剤、沈降調整剤、防曇剤、耐熱剤などがあげられる。

記録媒体は特に限定されるものではなく、従来から使用されているサイズ加工のないかあるいは細サイズの紙、一般に上製紙として

市販されているサイズ加工された紙、中質紙、和紙、木紙、アセナート、アイロン等の紙およびそれらの繊維でつくられた織物、ポリビニルアルコール、ポリビニルピロリドン、ニセルセルロース等の親水性の高分子化合物を表面に塗布したポリエステル、ポリカーボネート等のプラスチックフィルムが記録媒体の例として挙げられる。親水性の点から特に本発明方法で好ましいのは、サイズ加工された紙および織物に対して印字を行なう場合である。

本発明のインクジェット記録方法は、これら有機カチオン性化合物含有溶液（有機カチオン性化合物を含有する無色又は淡色の液体）、インク（アニオン性基を有する染料を含有するインク）および記録媒体を用い、先ず、有機カチオン性化合物含有溶液をインクによって印字を行なうのに先立って（或はしくは印字を行なう直前に）記録媒体に付着せしめ、特に記録媒体を加熱したり強制的な乾燥を行

なうことなく、有機カチオン性化合物含有溶液を付着せしめた部分に淡色のインクを付着せしめることによって、染料中のアニオン性基と有機カチオン性化合物中のカチオン性基とが結合して固着に不溶又は固着の強が形成され、これが強固として表われるというものである。

有機カチオン性化合物含有溶液を記録媒体に付着せしめる方法としては、スプレー、ローラーにより記録媒体の全面に有機カチオン性化合物含有溶液を付着せしめる方法、記録媒体を有機カチオン性化合物含有溶液に浸漬した後スクイズローラー等により余剰の有機カチオン性化合物含有溶液を絞り取る方法などが考えられるが、有機カチオン性化合物含有溶液を後にインクが付着される部分にのみ選択的に付着させかつその溶液を均一に塗布しうるインクジェット方式により行なわれるのが最も好ましい。

ただし、有機カチオン性化合物含有溶液を

インクジェット方式により付着せしめる場合にも、有機カチオン性化合物含有溶液の1滴が記録媒体上で形成するドット径と、インクの1滴がつくるドット径とがほぼ等しければ、有機カチオン性化合物含有溶液を選択的に付着せしめる時に、有機カチオン性化合物含有溶液の付着させる位置とインクが付着する位置とが完全に一致しなくてはならないので、両者の照射位置の調整が困難である。従って（a）有機カチオン性化合物含有溶液を噴出するノズルの径をインクの噴出するノズルの径よりも大きくする、（b）有機カチオン性化合物含有溶液の粘度をインクの粘度よりも低くしてインクと同条件で吐出せしめた時にインク滴よりも有機カチオン性化合物含有溶液の滴の径が大きくなるようにする、等の方法により有機カチオン性化合物含有溶液の記録媒体上での有機カチオン性化合物含有溶液のドット径をインクのドット径と比較して大きくしておく方が好ましい。あるいは（c）有機カ

チオン性化合物含有溶液とインクとのドット径に差をつけることが困難な場合にはインクの印字位置を処理することにより、インクが付着される部分よりも例えば1ドット分画像の周辺に余分に有機カチオン性化合物含有溶液を付着する方法が好ましい。

有機カチオン性化合物含有溶液が無色又は淡色でなければならぬ一つの理由は、前記のとおり、有機カチオン性化合物含有溶液がインクの付着により形成される画像の周辺にも付着せしめるためである。有機カチオン性化合物含有溶液が無色又は淡色でなければならぬもう一つの理由は、印字された（形成された）画像がインクだけで印字したものとほぼ同一にするためである。そうしたことから、これらが同色とならない範囲で有機カチオン性化合物含有溶液は実質的に無色又は淡色であればよく、換言すれば、画像周辺への有機カチオン性化合物含有溶液の付着が原因でできない程度、特にカラー画像を形成した場

合に色再現が不良とならない程度に顔色又は顔色で塗れば良い。

有機カチオン性化合物含有溶液を記録媒体に付着せしめ、続いてインクを付着させるまでの時間は印字品質(画像品質)に影響を与える重要な要因である。この時間は有機カチオン性化合物含有溶液およびインク中の溶媒の移行速度、有機カチオン性化合物含有溶液の記録媒体中への浸透速度、インクの表面張力等の要因により適当な範囲が与えられる。最も好ましいのは有機カチオン性化合物含有溶液が記録媒体に浸透し、記録媒体表面に見かけ上有機カチオン性化合物含有溶液がなくなった直後からその数秒後の間にインク滴が付着されることである。インク滴を付着する時に有機カチオン性化合物含有溶液が記録媒体表面に残っていると、インクの飛散による画像周辺の汚れが発生したり、インクが有機カチオン性化合物含有溶液層に移行して画像にじみが生じたりし易い。逆に、有機カ

チオン性化合物含有溶液の付着から時間が経過し過ぎると、有機カチオン性化合物含有溶液中のカチオン性基とインク中の染料のアニオン性基と反応が速くなったり、有機カチオン性化合物含有溶液中の浸透剤の効果が小さくなりインクの着色が遅くなったりしてしまふ。

インクが付着する時の有機カチオン性化合物含有溶液の付着状態を制御するためには、プリンターにおける有機カチオン性化合物含有溶液を吐出せしめるヘッドとインクを吐出せしめるヘッドとの相対位置の調整、有機カチオン性化合物含有溶液への浸透剤の付加量の調整を行えば良い。

有機カチオン性化合物含有溶液およびインクを記録媒体に付着せしめるには、種々提案されているインクジェット方式を用いることができる。これらの方式については例えば前田 淳次氏の提案に係るテレビジョン学会誌31(7)540(1983)にも記載されている。代表的

な方式は荷電受制御形の遠射噴射方式：カイザー式、グループ式、バブルジェット式、ステンメ式などのオンディマンド方式である。

なお本発明に類似したものとして特開昭54-43733号公報に記載された方法があるが、これは本質的にガラス上で2酸化窒素の成分の組合わせにより反応させ固着させるというものである。加えて、ここでインクは油性であり、かつ、実施例に記載されているイソシアネートあるいはエポキシ基等は本質的に不安定であり、ノズル目詰まり等の点で一般プリンターには不適である。

実施例

(ここで%は重量基準である。)

まず下記の処方によって8種の有機カチオン性化合物含有溶液、19種のインク(5種のイエローインク、7種のマゼンタインク、5種のシアニンインク、2種の黒色インク)を調製した。

(有機カチオン性化合物含有溶液P-1)

ボリアリルアミン	5.0%
グリセリン	10.0%
エチレングリコール	11.0%
ジエチレングリコール	20.0%
ジエチレングリコール モノブチルエーテル	12.0%
デヒドロ硫酸ソーダ	0.1%
精製水	残部

(有機カチオン性化合物含有溶液P-2)

ポリエチレンジイミン	3.0%
グリセリン	10.0%
ジエチレングリコール	23.0%
ジエチレングリコール モノフェニルエーテル	5.0%
デヒドロ硫酸ソーダ	0.1%
精製水	残部

(有機カチオン性化合物含有溶液P-3)

前記P-1のボリアリルアミンにかえて四級ポリマー(N-トリメチルアミノメチルポリスチレン：前記式(10)で $m=1$ 、 $R'=$

$R^* = R^* = -CH_3$ としたもの)を用いたもの。

(有機カチオン性化合物含有溶液 P-4)

前記 P-2 のポリエチレンイミンにかえて
テトラエチレンペンタミンを用いたもの。

(有機カチオン性化合物含有溶液 P-5)

ポリジメチルジアリル アンモニウム塩	4.0%
グリセリン	10.0%
エチレングリコール	11.0%
ジエチレングリコール	32.0%
デヒドロ酢酸ソーダ	0.1%
精製水	残部

(但し NH_4OH で $pH=13.5$ に調整した。)

(有機カチオン性化合物含有溶液 P-6)

ポリアリルアミン	4.0%
グリセリン	5.0%
ジエチレングリコール	25.0%
プロピレングリコール モノブチルエーテル	1.0%
精製水	残部

(但し $(C_2H_5)_4NOH$ で $pH=13.5$ に調整した。)

を用いたもの。

(イエローインク Y-4)

C. I. アシッド・イエロー-17	3.0%
グリセリン	10.0%
エチレングリコール	15.0%
ジエチレングリコール	28.0%
デヒドロ酢酸ソーダ	0.3%
精製水	残部

(イエローインク Y-5)

C. I. アシッド・イエロー-23	3.0%
グリセリン	5.0%
ジエチレングリコール	22.0%
ジエチレングリコール モノブチルエーテル	3.0%
2-ピリジンチオール-1- オキシドナトリウム	0.2%
精製水	残部

(マゼンタインク M-1)

前記インク Y-1 の C. I. アシッド・イエロー-23 にかえて C. I. アシッド・レッド 82 を用いたもの。

(イエローインク Y-1)

C. I. アシッド・イエロー-23	3.0%
グリセリン	10.0%
エチレングリコール	15.0%
ジエチレングリコール	24.0%
ジエチレングリコール モノブチルエーテル	4.0%
デヒドロ酢酸ソーダ	0.3%
精製水	残部

(イエローインク Y-2)

C. I. フード・イエロー-3	3.0%
グリセリン	10.0%
エチレングリコール	15.0%
ジエチレングリコール	26.0%
プロピレングリコール モノブチルエーテル	2.0%
デヒドロ酢酸ソーダ	0.3%
精製水	残部

(イエローインク Y-3)

前記インク Y-1 の C. I. アシッド・イエロー-23 にかえて C. I. ダイレクト・イエロー-142

(マゼンタインク M-2)


前記インク Y-2 の C. I. フード・イエロー-3 にかえて C. I. アシッド・レッド 254 を用いたもの。

(マゼンタインク M-3)

前記インク Y-1 の C. I. アシッド・イエロー-23 にかえて C. I. アシッド・レッド 35 を用いたもの。


(マゼンタインク M-4)

前記インク Y-2 の C. I. フード・イエロー-3 にかえて下記構造式 (A) の染料を用いたもの。



(マゼンタインク M-5)

前記インク Y-1 の C. I. アシッド・イエロー-23 にかえて下記構造式 (B) の染料を用いたもの。



…(B)

(マゼンタインクM-6)

前記インクY-4のC.I.アシッドイエロー-17にかえてC.I.アシッド・レッド35を用いたもの。

(マゼンタインクM-7)

前記インクY-5のC.I.アシッド・イエロー-23にかえて上記構造式(A)の染料を用いたもの。

(シアニンクC-1)

前記インクY-1のC.I.アシッド・イエロー-23にかえてC.I.ダイレクト・ブルー86を用いたもの。

(シアニンクC-2)

前記インクY-1のC.I.アシッド・イエロー-23にかえてC.I.ダイレクト・ブルー9を用いたもの。

また、これらとは別に1種の有機カチオン性化合物含有溶液(Q-1)と、4種のインク(イエローインクY'、マゼンタインクM'、シアニンクC'及び黒色インクB1')を調製した。

(有機カチオン性化合物含有溶液Q-1)

ポリアリルアミン	4.0%
グリセリン	10.0%
エチレングリコール	11.0%
ジエチレングリコール	32.0%
精製水	43.0%

(但しNaOHでpH=8.0に調整した。)

(イエローインクY')

C.I.アシッド・イエロー-23	3.0%
グリセリン	10.0%
エチレングリコール	15.0%
ジエチレングリコール	14.0%
ジエチレングリコール モノブチルエーテル	14.0%
デヒドロ酢酸ソーダ	0.3%
精製水	残部

(シアニンクC-3)

前記インクY-2のC.I.フード・イエロー3にかえてC.I.ダイレクト・ブルー86を用いたもの。

(シアニンクC-4)

前記インクY-4のC.I.アシッド・イエロー-17にかえてC.I.ダイレクト・ブルー86を用いたもの。

(シアニンクC-5)

前記インクY-5のC.I.アシッド・イエロー-23にかえてC.I.ダイレクト・ブルー249を用いたもの。

(黒色インクB1-1)

前記インクY-1のC.I.アシッド・イエロー-23にかえてC.I.フード・ブラック2を用いたもの。

(黒色インクB1-2)

前記インクY-5のC.I.アシッド・イエロー-23にかえてC.I.アシッド・ブラック72を用いたもの。

(このインクY'は前記インクY-1中のジエチレングリコールモノブチルエーテルを増量したものである。)

(マゼンタインクM')

前記インクY'のC.I.アシッド・イエロー23にかえてC.I.アシッド・レッド92を用いたもの。

(シアニンクC')

前記インクY'のC.I.アシッド・イエロー23にかえてC.I.ダイレクト・ブルー86を用いたもの。

(黒色インクB1')

前記インクY'のC.I.アシッド・イエロー23にかえてC.I.フード・ブラック2を用いたもの。

これら有機カチオン性化合物含有溶液及びインクを用い、カイザー型オンディマンドインクジェットプリンター或いは荷電制御型インクジェットプリンターによって紙-1に示したごとく印字を市販の上質紙に行なった。

表 - 1

No.	印字方式	有機カチオン性化合物含有溶液	インク			
			イエロー	マゼンタ	シア	ブラック
1	O	P-1	Y-1	M-1	C-1	B1-1
2	O	P-2	Y-2	M-2	C-3	B1-1
3	O	P-3	Y-3	M-3	C-2	B1-1
4	O	P-4	Y-4	M-6	C-4	B1-1
5	O	P-5	Y-2	M-2	C-2	B1-1
6	O	P-1	Y-3	M-4	C-2	B1-1
7	O	P-3	—	M-5	—	—
8	C	P-6	Y-5	M-7	C-5	B1-2
9	O	なし	Y-1	M-1	C-1	B1-1
10	C	なし	Y-5	M-7	C-5	B1-2
11	O	Q-1	Y-1	M-1	C-1	B1-1
12	O	なし	Y'	M'	C'	B1'
13	O	Q-1	Y-4	M-6	C-4	—
14	O	Q-1	—	M-5	C-4	—

注1) 印字方式で、Oとあるのはオンディマンド方式、Cとあるのは荷電制御方式を指す

ヘッド部31Y、31M、31C、31Bに供給され、各色顔料に応じてヘッドに取り付けられた送液ノズル（図示せず）に圧力が印加されて記録紙（記録媒体）4上に画像が形成される。図中、5はプラテンである。

有機カチオン性化合物含有溶液を供給するためのヘッド31Pはキャリッジ1のインク用のヘッド31y、31m、31c及び31bの下部に取り付けられており、記録媒体4が上方に走査されるため、相対的に有機カチオン性化合物含有溶液がインクよりも先に記録媒体4に付着されるように設計されている。また、有機カチオン性化合物含有溶液はイエローマゼンタ、シア、ブラックのいずれかの画像が印字される部分の画像に対応し、その画像の周辺に1ドット分だけ余分に吐出されるように画像が処理される。図4図は有機カチオン性化合物含有溶液の付着部分

している。ここで、これらプリンターの紙面は次のとおりである。

(1) カイザー型オンディマンドインクジェットプリンター

直径60 μ mのノズルおよびインク室、送液子を9個有するヘッドを5個用いる。それぞれ有機カチオン性化合物含有溶液、イエローインク、マゼンタインク、シアインク、ブラックインクの供給を行なうのに使用した。図1図はプリンターキャリッジ部の平面図、図2図はキャリッジ部の側面図、図3図はヘッド（1個）の正面図である。キャリッジ1はシャトル2上を走査（図1図に示した矢印方向に走査）され、キャリッジ1上に設けられた有機カチオン性化合物含有溶液用カートリッジ3Pから有機カチオン性化合物含有溶液がそのヘッド部31Pに供給され、また、インク用カートリッジ3Y、3M、3C及び3Bよりインクがそれぞれの

(P)にインクが付着され画像(1)が形成された状態を示している。

(2) 荷電制御型インクジェットプリンター

図5図のような2液荷電制御型インクジェット・ユニットを5個用いる。図6図に示すプリンターで印字を行なった。キャリッジ1内の各インク用のプリントヘッドの配置は図7図のようにした。ノズルは直径25 μ mのものを用い、粒子化周波数は132KHzとした。

注2) No.11、No.13及びNo.14は参考例である。No.9、No.10及びNo.12は比較例である。なお、No.14は有機カチオン性化合物含有溶液用ヘッドにM-6又はC-4のインクを入れておき、Q-1液をイエローインク用ヘッドに入れて印字したもの（インクによる印字後、耐水化剤の入った液を付着させるもの）である。

印字結果は表-2のとおりであった。

	温度湿度				乾燥時間 (sec)	温度 にじみ	色調	産物の 特性	インクの張面力 (dyn/cm (25°C))
	Y	M	C	B					
1	0.77	1.03	1.08	1.04	8	7	2	5	39~41
2	0.73	1.05	1.04	1.07	5	4	2	3	42~44 (B16Cを抜く)
3	0.73	1.01	1.05	1.07	2	14	3	11	39~41
4	0.76	0.96	1.05	1.05	16	13	5	9	52~57 (B16Cを抜く)
5	0.71	1.03	1.07	1.05	8	6	3	10	40~42
6	0.72	1.01	1.00	1.07	4	3	6	5	40~42
7	—	1.00	—	—	—	0	—	—	30
8	0.73	0.99	1.04	1.03	7	3	2	8	42~44
9	0.84	0.93	0.92	0.93	57	30	48	45	30~41
10	0.70	0.99	1.00	0.99	62	65	51	48	41~44
11	0.69	0.95	0.94	0.93	6	5	2	5	36~41
12	0.65	0.90	0.84	0.92	53	76	45	40	31~33
13	0.74	0.98	1.05	—	4	7	4	—	51~57
14	—	0.93	0.93	—	—	5	2	—	55~57

ものを○、またこれらに明らかな差があるものを×とした。

- 注7) 図版の鮮明性は2色版中のベタ版位
部で図版周辺のインクの洩れ出しの
有無を目視で判定し、洩れのあるも
のを×、洩れの無いものを○とした。
- 注8) ノズルの目詰りテストは印字した後、
印字操作を休止したままで20℃、65
%RHの環境で2か月間放置し、放
置後再び正常な印字が可認が否かを
調べた。○は目詰りなし、×は目詰
りありを我わしている。
- 注9) 保存性はインクおよび有機カチオン
性化合物含有溶液をポリエチレン瓶
の容器に入れ-20℃、4℃、20℃、5
0℃、70℃のそれぞれの条件下で3
か月間保存し、保存前後の粘度、張
力、電気伝導度の変化、および
沈降物析出の有無を調べた。○は保
存性良好、×は保存性不良を我わし

特種昭 63-299971 (13)

- 注1) Yはイエロー顔料、Mはマゼンタ顔料、Cはシアン顔料、Bは(Black)は黒色顔料を指している。
- 注2) 顔料濃度はベタ部をマクベス濃度計で測定した。
- 注3) 顔料の耐水性は顔料サンプルを30度の水に1分間浸漬し、浸漬前後の顔料濃度をマクベス濃度計で測定し、下式により退色率を求めた。
- $$\left(1 - \frac{\text{浸漬後の主色濃度}}{\text{浸漬前の主色濃度}}\right) \times 100(\%)$$
- 注4) 乾燥時間は印字機速さにインクが乾きなくなるまでの時間を測定した。
- 注5) 顔料にじみはフェザリングの有無を目視にて判定した。×はフェザリングあり、○はフェザリングなしを意味している。
- 注6) 色調は目視で判定し、ここで有機カチオン性化合物含有精液の付着が認められるか、ほとんど認められないこと、及び、なしと色調に大差ない

ている。

〔効 果〕

本発明のインクジェット記録方法によれば下記の
記のような効果がもたらされる。

- (イ) インク中の染料と有機カチオン性化合物
含有溶液中のカチオン性基とが結合し、有機
カチオン性化合物を媒介として染料が結合し、
水不溶の集合体を形成するため、画像の耐水
性が著しく向上する。
- (ロ) 染料が集合体となるため、染料が紙の内
部まで浸透せずに紙の表面近傍にとどまるた
め、画像の鮮明性、濃度が向上する。また紙
の裏面方向にも濃度が浸透するのみで染料が
紙がらないためシャープネスがよく、解像度
の高い画像が得られる。
- (ハ) 染料が集合体となるため上記のように紙の
裏面方向への色材の浸透が抑えられるため、表
面張力が低く乾燥しやすいインクを用いても画
像にじみを生じない。従って乾燥性を向上で
きる。

(二) 有機カチオン性化合物含有溶剤中の促進剤により表面張力の高いインクを用いても乾速性は高まる。

(ホ) 染料と有機カチオン性化合物との複合体の耐光性は染料が複合体を形成しない場合に比較して向上する(但し、理由は明らかになっていない)。

(ヘ) 耐水性を考慮せずにインクに使用する染料が選択できるため耐ノズル目詰り性、色味の改良が可能である。

4. 図面の簡単な説明

第1図はカイザー型オンディマンドインクジェットプリンターのキャリッジ部の平面図、第2図はその側面図、第3図はインクヘッドの正面図である。

第4図は記録媒体上に画像形成(印字)がなされた様子を表わした図である。

第5図は2値有電制御型インクユニットの概略を示した図、第6図はこのユニットを採用したプリンターで印字を行なう様子を表わした図

6…インクポンプユニット

71…有電電極

72…無電電極

8…ガード

特許出願人 株式会社リコー
代理人 井理士 佐田 守 横井1名




である。


第7図はプリントヘッドの配置を示した図である。

- 1…キャリッジ
- 2…シャトル(キャリッジガイド)
- 21…キャリッジ送りネジ
- 3P…有機カチオン性化合物含有溶剤カートリッジ
- 3Y…イエローインク用カートリッジ
- 3M…マゼンターインク用カートリッジ
- 3C…シアンインク用カートリッジ
- 3B…黒色インク用カートリッジ
- 31…ヘッド
- 31P…有機カチオン性化合物含有溶剤用ヘッド
- 31Y…イエローインク用ヘッド
- 31M…マゼンターインク用ヘッド
- 31C…シアンインク用ヘッド
- 31B…黒色インク用ヘッド
- 4…記録媒体
- 5…プラテン(ドラム)


第1図



第2図




第3図




第4図



第5図



第 6 図



第 7 図

